

Petroleum Jelly Cosmetic Grade

METHOD	VALUE/RESULTS	PROPERTIES
Kinematic Viscosity @ 100°C	6 cst	ASTM D445
Congealing Point	55.2°C	ASTM D938
Penetration	More than 130 (0.1 mm)	ASTM D1321
Color (Lovibond)	1.0 y	IP-17 METHOD A 2" CELL
Acidity or Alkalinity	According to the test method	B.P 2007
Drop Melting Point	58°C	ASTM D127
Sulphated Ash	Less than 0.05%	B.P 2010
Flash Point	214°C Min.	ASTM D92
Specific Gravity @ 60°C	0.822	USP
Odor	Less when rubbing on skin	—

Phone: (+98)3132684505

Cell Phone : +989910174908

<http://PersiaParaffin.com>

E-mail: info@persiaparaffin.com